

High performance thermal properties of natural pumice-based bricks

Miguel Galván-Ruiz^{1,2*}, Marco Zaleta-González¹

¹*División de Investigación y Posgrado, Facultad de Ingeniería. Universidad Autónoma de Querétaro. CU Cerro de las Campanas 76010, Querétaro, México.*

²*CETIS 105-SEP. km 3.5 Carretera Tlacote 76138, Querétaro, México.*

*Corresponding author: Email: mgr@uaq.edu.mx

* Tel.: +52 442 1789777; fax: +52 442 1921200 ext. 6023.

ABSTRACT

Aims: Characterization of the thermal properties of natural pumice-based lightened bricks under ASTM standards, analyzing thermal conductivity to promote thermal comfort inside buildings.

Study design: The project had four stages. The first was getting the base material (pumice). The second was developing of lightened test specimens. The third was focused on the characterization and fourth intended for the interpretation and analysis of the test results and conclusions of the project.

Place and Duration of Study: Universidad Autónoma de Querétaro, from January to December, 2012.

Methodology: XRD by powders with a diffractometer Bruker D-8 Advance, Cu anode at 30 KV and 30 mA, Cu Ka radiation $\lambda = 1.54 \text{ \AA}$, from 10 to 90° on the 2 θ scale at 2°/min. Mechanical tests according to ASTM C109/C109M-08, minimum compressive strength at 28 days of 7.8 N/mm². X-Ray fluorescence with Spectrometer SIEMENS fluorescence X-ray SRS 3000. Thermal conductivity using ASTM C177: Standard Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded Hot-Plate Apparatus (2004).

Results: Pumice was identified as pozzolanic material with crystalline phases of significant silica-aluminate content by X-Ray diffraction. X-Ray Fluorescence analysis confirmed the elements of the pumice, therefore this analysis confirmed the presence of Si dominant, followed by Al. Lightened bricks were developed meeting the specifications of resistance of the ASTM standards, and the properties of thermal conductivity are better than traditional sand-cement bricks; density and porosity could create a zone of thermal comfort within buildings. Apparent thermal conductivity of pumice specimens was 0.336W m⁻¹K⁻¹, thermal resistance 0.234W⁻¹m²K and Expanded uncertainty (k=2) 5%.

Conclusion: Due to porosity together with good worthy mechanical comportment, the natural pumice-based bricks have advantages in lighter weight-effort, tensile strength and higher thermal insulation characteristics. The analyzed pumice reduces the thermal conductivity results 66% lower than hollowed coefficient of lightened bricks, 59% lower than typical. Thermal conductivity of lightweight bricks and lower elaborated in 62% than traditional mud brick. The thermal properties of the this work implies a superior insulation material are affected by, comparable to the size of the mineral material form, presence of micro-pores, fractures, and humidity highest quality insulation materials.

Keywords: Natural pumice, bricks, thermal properties, energy efficiency.

1. INTRODUCTION

Due to its relatively low thermal conductivity characteristics and being a local product, pumice aggregate concrete (PAC) blocks are increasingly used as a masonry wall unit [1]. The masonry construction is the most widely used worldwide globally, and especially it is particularly useful in Latin America has a beneficial use; an example of this are ancient pre-Hispanic buildings that still standing and preserved both architectural beauty attractiveness and its goal of structural support [2]. Similarly, public buildings and colonial faithful heritage are clear testimony of the quality and durability that masonry construction systems can provide [3]. However, the construction industry continues

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Font: 10 pt, Superscript

Formatted: Font: 10 pt, Superscript

Formatted: Font: 10 pt, Superscript

Formatted: Font: 10 pt, Superscript

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

*Corresponding author: Email: mgr@uaq.edu.mx

* Tel.: +52 442 1789777; fax: +52 442 1921200 ext. 6023.

improving the structural building systems according to the available technology; this technological development, due to the increasingly demanding requirements for quality and environmental standards for buildings [4]. Technological advances in masonry walls are to reduce the construction execution times in construction; improve thermal insulation, sound insulation, fire protection and reduction of reducing coating thickness [5]. Many of these advances are focused in getting a more sustainable building system by reducing costs for energy consumption [6, 8, 24]; however, [6]. Nevertheless, environmental development and application of natural materials that meet meeting the nowadays sustainable requirements remain being a problem. [7].

Formatted

... [1]

Buildings have resources consumption needs; the electric energy is the most demanding requirement, because of high energy consumption required by the heating, ventilation, and air conditioning (HVAC) systems for maintaining internal thermal comfort, and hinder the outside temperature due to inside buildings increased temperatures reach up to 2°C [8]. Different kind of masonry walls has been investigated to provide a thermal isolation structure for buildings, and lightweight bricks walls have demonstrated this capacity; [9]; approximately 70% of total energy consumption is destined to HVAC systems hence; henceforward, savings in air conditioning and heating are a significant cost savings in the maintenance of buildings [7, 10].

Formatted

... [2]

Combination of the heat storage capacity and the thermal insulation characteristics of the masonry walls regulate, stabilize the conditions inside the building construction. The thermal behavior of masonry walls depends on the conductivity coefficient of the wall material, as well as the thermal characteristics of the mass of the wall [9, 10]. The qualities of thermal inertia of the wall slows the response to changes in external conditions and limit changes in internal temperature, so that, as a consequence when constructing walls with bricks, which by their physical properties of the matter have low conductivity coefficient, a thermal isolation will be provide provided to the building a thermal isolation from its conception [10, 11].

Formatted

... [3]

According to P. Ihm (2012) it is necessary to make essential intend a materials design optimization, in order to achieve the energy efficient [14] but those elements for structural efficiency [12]. Even though, the insulation show a high investment cost that materials are usually expensive and most people are not willing to pay. In addition, these novelty elements as lightweight and semi lightweight concretes using materials and construction processes, require trained staff and usually are not available skilled labor [45]. [16]. Despite [13], [14]. In the good results that show temperature insulation new materials and methods used to date, these have significant disadvantages, specifically the main is high cost of the material, unusual constructions. For another part same way, the septum annealing is the leading and most abundant construction material [17] but [15], although, their process of making processing has a the disadvantage of high cost in ecological terms, it needs a temperature between impact as a result of prerequisite temperatures from 950°C and to 1050°C for 12 hours, requires requiring 2365 kJ= 657 W/h, and the type of fuel used, typically fossil fuel [18] used [16]. The benefits of use natural material use become evident when considering that for every MW/h of renewable energy generated, the emission of approximately 0.75 T of CO₂ is avoided [25], and a "model" tree can absorb 0.67 T of CO₂ [26, 17].

Formatted

... [4]

As a result, this work searches for low-cost new construction materials with better properties. The benefits of thermal insulation and sufficient availability and accessibility which are one of the main goals for this study.

Formatted: Not Highlight

Natural materials shows the lowest natural material use become evident; thermal conductivity and the fiber variety contribute significantly to improving improve the thermal insulation properties to be applied to the exterior of buildings [11, 12, 13, 18]. Furthermore, the

coefficient of thermal conductivity depends on the humidity, layer thickness and porosity of the material. A [19]. In the same way, high porosity has considerable impact on the thermal performance of insulation materials.

[20]. The walls of lightweight material with pumice bricks could have a density between 650 and 685 Kg/m³, the Young's modulus ranges from 6,850 to 7,580 MPa, and a thermal conductivity coefficient between from 0.17 and to 0.19 Wm⁻¹ K⁻¹ [19]. Although [21]. Afterward, research shows demonstrate the potential of the mineral pumice because there has only been applied in the form of wall construction as a structural element, but used as a coating, it has proved that produce worthy thermal qualities effects in essential processes in the area of the baking ovens for isolation/insulation of the burn chamber [20]. Despite the. Whereas he widely knowledge of pumice, it is necessary to make achieve a physicochemical-chemical characterization of Querétaro the Querétaro State pumice that allows discovering the nature of, providing local pumice in this region properties for better construction practice.

Faced with the resources consumption of resources for raw materials and excessive air pollution environment impact, care for them is increasing to a greater degree than in the past. In recent years, some researches about natural materials have shown to be commensurate/adequate along with common building materials [44][18]. Lightened bricks lightened with made of natural materials still having the typical characteristic disadvantage of low compressive strength, although having good isolation results, some of pumice lightened bricks investigations [8], [19], evidence the unfortunately the constant failure of mechanical properties [21]. One of the natural materials with the qualities quality for construction is the pumice; applied both for their physical and mechanical properties [24] to improve the thermal resistance of the structures and lower total loads. [22]. The walls made of pumice as raw material for hollow walls, has have proved to be one of the most effective ways to reduce energy consumption and costs due to the non-use of air conditioning systems, providing that proper thickness of material is used [22]. This work deals with lightweight pumice bricks theme which approves the NMX standards for structural bricks and ASTM standards about [23]. The main objective of this paper is the examination of high performance thermal conductivity properties of natural pumice-based bricks which provide a better thermal isolation material. The principal objective is to create a lightweight pumice-based brick with the characteristics before mentioned insulation properties, appropriate availability and user-friendliness.

Hypothesis: the local pumice rock in natural extraction natural form as aggregated an aggregate for lightweight bricks provides an efficient isolation natural material with a thermal conductivity coefficient lower than typical lightweight bricks improving approving the compressive strength/mechanical required by currently standards.

2. MATERIAL AND METHODS / EXPERIMENTAL DETAILS / METHODOLOGY (ARIAL, BOLD, 11 FONT, LEFT ALIGNED, CAPS)

2.1 Material

In this study was characterized the pumice rock which from the superficial mine of San Clemente, Querétaro. Querétaro State was characterized. Pumice is a glassy igneous rock with low density and high porosity ratio, with color tones ranging from white to gray. Contains mainly Mainly contains silica-aluminates and has a visually appearance from crushed texture to vitreous; usually could be found in considerable bulk volumes as a result of volcanic action/volcanism. Pumice has different applications; can be found in art works of art, in the health and beauty industry mainly and in construction and, mainly as decorative materials of low density

Formatted: Font: 10 pt, Superscript

Formatted: Font: 10 pt, Superscript

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

textured coatings. The pumice is a result of volcanic activity, and may be acidic or alkaline in composition; density varies between from 0.5 and to 1 T/m³ for acid rock, and between from 1 and to 2 T/m³ for alkaline pumice. It has approximately 70% porosity.

2.2 Methods

2.2.1 Analysis of the crystalline phases by XRD

Pumice preparation for XRD study according to the methodology of SCT standard M-MMP-1-03-03. Ten random samples from the bank of San Clemente mine in Queretaro were analyzed in two different conditions. The first was in a natural extraction condition and the second after a calcination process at 450°C during 4 hours into a muffle. Two analyzes were conducted on each sample with the XRD powder process in a diffractometer Bruker D-8 Advance, with Cu anode operated at 30 KV and 30 mA, wavelength of Cu Ka radiation of $\lambda = 1.54 \text{ \AA}$, from 10 to 90° on the 2θ scale at 2° / min. The calcination process was made in order to remove the organic content of the samples.

2.2.2 Compressive strength

Mechanical tests are according to ASTM C109/C109M-08 and NMX-C-036/404 which establishes a minimum compressive force at 28 days of 7.8 N/mm². With Formerly, with the natural pumice were created 5 produced five gravels with different granulometry. Then Afterward, three different proportions were analyzed with of each kind of gravel. On each mixture Subsequently were made three bricks in a manual press and were elaborated to test tested at ages of 7, 14 and 28 days. The bricks Finally, the mixtures showing appropriate compressive results, were made in a manual press and the mixture which showed better properties according to this investigation was selected to continue with proceed to the thermal conductivity test. The proportions are in Table 1, proportion results are shown.

Table 1. Proportions used for samples in the compressive strength test.

N° of Samples	Cement (%)	Pumice (%)	Gravel (Type)
	9	40	60
	9	50	50
	9	60	40

G1 to G5

2.2.3 X-Ray Fluorescence

X-ray spectrometry is a qualitative and quantitative elemental analysis based on the lengths of wave or X-ray energy, emitted by the sample after primary radiation. X-Ray fluorescence was done with Spectrometer SIEMENS fluorescence X-ray SRS 3000, method based on ASTM standards [26][24].

2.2.4 Thermal conductivity

Thermal conductivity using the ASTM C177: Standard Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded Hot-Plate Apparatus (2004)[GHPA] [23]. The primary apparatus GHPA provided by the National

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Font: 11 pt, Bold

Formatted: Left

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Font: Helvetica, Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Space Before: 3 pt, After: 3 pt

Formatted Table

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Metrology Center (México), to determine measure the resistance and the apparent thermal conductivity of insulating materials, is shown in Figure 1 shows a picture of the apparatus, provided by the CENAM for this research.

Principle of Operation: the GHPA (Figure 4) is a basic tool that uses the approach of conduction heat transfer in a steady state and to determine the thermal conductivity by the following equation:

$$q \lambda = l / (A \Delta T) \quad (1)$$

Where q is the ratio of heat flow through the sample W , λ is the thermal conductivity of the sample in $W / m K$; ΔT is the temperature difference across the sample $^{\circ}C$ K or L is sample width in m and A is the cross sectional area in m^2 .



Figure1. Guarded hot plate apparatus (GHPA). National Metrology Center, México.

Procedure for assessment

The procedure for measurement can be summarized in the following stages:

1. Sample selection,
2. Sample preparation and installation in the apparatus,

203 3. Establishing constant state thermal
204 4. Data collection and
205 5. Analysis of results.
206

Formatted: Not Highlight

207 Sample elaboration: Samples were made in a cylindrical metallic mold with 19 cm of
208 diameter and 7.86 cm of thick, helped by a universal machine. The mixture is poured into the
209 mold and cylindrical mold and the machine's shaft is actuated. The universal machine stops
210 until it feels senses a slight resistance in the sample. The sample selected samples for the
211 thermal test were the samples made with the mixture that showed more approving ASTM
212 compress strength resistance standard, using the less amount quantity of cement. The
213 parameters controlled during the test were the minimum and maximum temperatures value,
214 simulating two extreme ambient local conditions.

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

215 The parameters controlled during the test were the minimum and maximum value for
216 temperature, simulating two extreme ambient conditions in Queretaro.

Formatted: Not Highlight

Formatted: Not Highlight

217
218 Sample Selection: the most critical factors in the selection of the sample are the size, width
219 and thickness, flatness and parallelism of the sample. The width is essential to keep the
220 error within the maximum allowed. The diameter should be chosen such that it fully covers at
221 least the size of measurement which is at least 152.4mm. The surfaces of the sample should
222 be flat and parallel to get a good thermal as possible, to improve the contact with GHPA
223 plates.
224

225 Sample Preparation: it is necessary to produce parallel sample surfaces to ensure good
226 thermal contact between it and the GHPA plates. The sample and thermocouples should
227 have rigid contact surface to a better determination of the temperature condition, and the
228 plates with the sample at a temperature close to the temperature of test, for example,
229 placing it in a furnace to prevent the absorption of condensation water. The dimensions and
230 weight were recorded previously to the test; the samples were tested in a dried weight
231 condition and in order to have this condition, the samples were dried in the furnace until get
232 a constant weight. After that, samples were covered with a thin plastic coat and placed in a
233 furnace to prevent the absorption of condensation water. Finally, the samples were placed in
234 an insulating foam mold that helps to reduce the lateral heat leakage and ensure a heat
235 unidirectional flow. The moisture of samples was controlled by this preparation. The relative
236 humidity was maintained at 32% during the test which is controlled by the GHPA as shown
237 in the test report.
238

Formatted: Not Highlight

Formatted: Not Highlight

239 Establishment of Permanent Thermal State: this stage begins after the installation of the
240 sample in the measuring area of the stored items and the insulating necessary needed to
241 reduce the effect of environmental conditions. The device takes action to fulfill accomplish the
242 conditions of temperature at which conditions to perform the test. The time required to
243 reach reaching steady state at a sample thickness of 25.4 mm and uniform insulating items is
244 almost 5 h; this time increases with if increasing thickness.
245
246

Formatted: Not Highlight

247 3. RESULTS AND DISCUSSION

248
249 Lighten practical building material by replacing a portion or all. The foregoing results show
250 advantages of the aggregates addition of the mix to make bricks, adding materials in excess
251 of 5% on the weight of the binder. These additions are a lightweight aggregate, which in this
252 case study is pumice. There is lightweight compound when the true density is less than
253 2g/cm^3 . Advantages of addition: the particle size inclusion improves by more reasonable
254 weight, higher, the physical characteristics were upgraded by reducing weight, sufficient
255 mechanical resistance and better satisfactory surface hardness. Moreover, the better quality

characteristics improve the thermal performance of blends with binders natural pumice-based bricks.

3.1 XRD

From XRD research on pumice samples, Figure 2 shows diffractograms from two natural samples and two samples after a burning process. The signals obtained are inconsistent and the graph shown vague so by XRD study did not support the total pumice formation, mostly due to the nature of their structure; presume result because the material include a vitreous fraction. This was confirmed through X-Ray fluorescence research.




Figure 2. Diffractograms of four of the pumice samples showing the main amorphous phase and the crystalline phases of signals which correspond essentially to silicon oxide.

When analyzing the samples after a burning process, diffractograms corresponding to those obtained in the first instance; in contrast, these diffractograms confirmed the amorphous phase of the material due to the presence of feldspar, a volcanic glass and phenol-crystals trace minerals, as hematite, with the remainder found in the second analysis of the crystal structures of predominantly silica-aluminates. Clear signals relative to crystalline phases of silicon oxide are shown in Table 2.

Table 2. Crystalline phases detected by XRD.

PDF	2θ	ID	Crystal
-----	----	----	---------

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Space Before: 3 pt, After: 3 pt

Formatted Table

086-1562 27.316 Silicon oxide phase 1 Quartz
41.55
70.23

085-0461 27.599 Silicon oxide phase 2

085-0459 27.31 Silicon oxide phase 3

083-0540	27.31	Silicon oxide phase 4	Quartz
081-0069	29.80	Silicon oxide phase 5	
	41.54		

063-7619	27.59	Silicon oxide phase 1	Low periodicity quartz
----------	-------	-----------------------	------------------------




Figure 2. Diffractograms of four of the t 252 en pumice samples showing the main amorphous phase and the crystalline phases of signals which correspond essentially to silicon oxide.

3.2 Compressive strength

The goal of this work focus on the property of thermal conductivity; however, proof of appropriate mechanical behavior across the study of compressive strength, which was suitable for use in manufacturing pumice bricks according to the typical practices. The compressive strength of specimens for 7, 14 and 28 days was analyzed according to the NMX-C-036-2004-ONNCCE "blocks, bricks—Compressive Strength—Test Method".ASTM

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Space Before: 3 pt, After: 3 pt

Formatted: Not Highlight

296 C109/C109M-08 standard. A total of 135 samples were tested under this NMX standard and
297 samples dimensions are 30 x 15 x 8 cm, length, width and thickness respectively. The finally
298 approved brick for next stage was the one that was made with 40% of cement and 60% of
299 pumice in weight. The area tested was 450 cm², with 3600 cm³ and a density of 0.720 T/m³.
300 Granulometry characteristics are showed in figureFigure 3. The values of compressive
301 strength and average gross section are according to standard NMX-C-404-2005-ONNCCE
302 "Blocks and Bricks partitions for structural purposes - Specifications and methods test".
303 Results are results are shown in Table 3. The mechanical characteristics of this lightweight
304 brick are especially relevant when it is take into account that almost any low-density brick
305 reaches the compressive strength required by NMX standards.
306
307

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Table 3. Results of compressive strength for specimens, averages.

Area (cm ²)	Resistance (kN)			Average resistance compressive strength (N/mm ²)		
	Age (days)			Age (days)		
	7	14	28	7	14	28
450	340.70	473.57	511.46	7.35	10.37	11.20

Table 4- Comparison shows values of compressive strength between some pumice-based lightweight bricks and ASTM C109/C109M-08 bricks and NMX-C-404-ONNCCE 2005 standards.

Piece	Compressive strength	Minimum compressive strength on gross area for blocks
	N/mm ²	
Own Lightweight Brick	6.52	
D1	2.80	Concrete block and septum annealing 6
E1	2.626	
E2	2.723	

Values of pumice-based lightweight bricks were taken from reference [19]. The most compressive force per unit of net cross-sectional area, exceed the specified compressive support for masonry; consequently, the material is a good choice for manufacturing lightened bricks.




Table 4. Compressive strength of pumice-based lightweight bricks, ASTM C109/C109M-08 standard.

Piece	Compressive strength	Minimum compressive strength on gross area for blocks
	N/mm ²	N/mm ²
Own Lightweight Brick	6.52	
D1	2.80	Concrete block and septum annealing
E1	2.626	6
E2	2.723	




Figure 3. Granulometry curve of gravel used for conductivity coefficient test.

3.3 X-Ray Fluorescence analysis

The elements in the pumice were confirmed, so XRF study by semi-quantitative percentages for each sample. The presence of Si foremost was long-established, followed by Al as shown in Table 5. It can be appreciated that the compound with the largest percentage is silicon oxide, the same as was detected in the past XRD study.

Table 5. Main elements detected by XRF.

Compound	Mass fraction (%w/w)
SiO ₂	75.958

Al ₂ O ₃	10.796
K ₂ O	8.537
CaO	2.428

3.4 Measurement of thermal conductivity

One of the most important factors in the thermal behavior of walls is the thermal conductivity of their bricks –[25]._Thermal conductivity for samples of building materials to the manufacture of lightweight bricks, consider the national standard thermal conductivity of insulating materialsASTM standards. The result of the thermal conductivity of the studied bricks helps for a more sustainable building. Conventional sand-cement bricks are around 0.930 W m⁻¹ K⁻¹. [26].

The thermal conductivity coefficient was measured in four samples. These samples were elaborated with the mixture which has the major compressive resistance, lower absorption and the best workability characteristics which ensured the use of the best mixture and the best thermal insulation conditions. To ensure the flatness in the samples, faces were filed until get parallel surfaces in all samples and the flatness and parallel conditions were confirmed with a surface measurement (Figures 4 and 5).



Figure 4. Pumice-cement sample 1.



Figure 5. Surface measurement.

The thermal conductivity of a material is a measure of its ability to transfer thermal energy (heat), by imposing a temperature gradient. Better materials enable delay in put heat and soften the outside temperatures, with air chambers or low density producing low thermal conductivity material. Results of thermal conductivity for pumice specimens are on Table 5.

Table 5. Experimental values of thermal conductivity.

NATIONAL METROLOGY CENTER	
Laboratory of Thermal Conductivity	
Operator: Saúl García Duarte	Test Number: One
SAMPLE DESCRIPTION: pumice-cement	
Identification: 1, 2	
Characteristics: solid material	
Dimensions: Samples of 19 cm diameter and 7.86 cm thick	
Notes: construction material	
APPARATUS DESCRIPTION: Guarded hot plate apparatus (GHPA)	
Orientation: Horizontal	
Operation mode: Double side measurement	
TEST PROCEDURE: Guarded hot plate apparatus with constant heat flux	
Experimental values:	
Variable name:	Average value:
Power dissipation during test / W	3.63
Hot plate temperature / °C	32.0
Cold plate temperature / °C	12.2
Temperature gradient in the sample / °C	19.8
Average temperature of test / °C	22.1
Ambient temperature / °C	21
Relative humidity / %	32
Sample thickness / mm	78.61
Measurement area / mm ²	21407
Average weight (1) / g	2275.1
Average weight (2) / g	2211.2
Results:	
Apparent thermal conductivity / W m ⁻¹ K ⁻¹	0.336
Thermal resistance / W ⁻¹ m ² K	0.234
Expanded uncertainty (k=2) / %	5

Formatted: Justified

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

NATIONAL METROLOGY CENTER	
Laboratory of Thermal Conductivity	
Operator: Saúl García Duarte	Test Number: One
SAMPLE DESCRIPTION: pumice-cement	
Identification: 1, 2	
Characteristics: solid material	
Dimensions: Samples of 19 cm diameter and 7.86 cm thick	
Notes: construction material	
APPARATUS DESCRIPTION: Guarded hot plate apparatus (GHPA)	
Orientation: Horizontal	
Operation mode: Double side measurement	
TEST PROCEDURE: Guarded hot plate apparatus with constant heat flux	
Experimental values:	
Variable name:	Average value:
Power dissipation during test / W	3.63
Hot plate temperature/°C	32.0
Cold plate temperature/°C	12.2
Temperature gradient in the sample /°C	19.8
Average temperature of test /°C	22.1
Ambient temperature/°C	21
Relative humidity /%	32
Sample thickness/mm	78.61
Measurement area/mm ²	21407
Average weight (1)/g	2275.1
Average weight (2)/g	2211.2
Results:	
Apparent thermal conductivity/W m ⁻¹ K ⁻¹	0.336
Thermal resistance /W ⁻¹ m ² K	0.234
Expanded uncertainty (k=2)/%	5

4. CONCLUSIONS

In this research brief and according to results, the objective examination of create a lightweight pumice-based brick with local pumice for masonry walls was achieved. Was also obtained an important conclusion that paves the way for future industrial exploitation high performance thermal properties of the Queretaro pumice is that the local pumice is suitable to produce lightweight natural pumice-based bricks in amounts from 50% to 70%, with the best mechanical performance at 60% of pumice content providing great thermal insulation properties was achieved as a consequence of thermal conductivity gotten in the experiments, in weight proportions that gives addition to the 7.35 N/mm² since 7 days and even achieve compressive resistance of 11.20 N/mm² at 28 days and improve, improving the resistance 86.67% major in specimens in over than minimum required by NMXASTM standards.

Natural In the same way, it is confirmed the amorphous phase of pumice as well as its dominant content of Si 75.95%, Al 10.796% and K 8.537% respectively. The low density of 0.792 T/m³ is equally important. High performance thermal properties of natural pumice-based bricks produce the expected technical capabilities for the thermal isolation insulation and mechanical properties, according to ASTM and NMX (Mexico) standards. Pumice from San Clemente, Queretaro, México, reduce The analyzed pumice reduces the thermal conductivity coefficient of lightened ordinary bricks which preferred to the traditional sand-cement bricks for keeping indoor temperatures stationary along climate changes during the

Formatted: Font: Bold, Font color: Auto

Formatted: Left

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

year. Lightweight brick elaborated in this work has $0.336 \text{ Wm}^{-1}\text{K}^{-1}$ of thermal conductivity coefficient which implies a better insulation material, is 66% lower than hollowed bricks, 59% lower than typical lightweight bricks and lower in 62% than traditional mud brick moreover present a lower density of 0.792 T/m^3 . Also after finalizing physic-chemical characterization methods, it is confirmed the amorphous nature of pumice as well as its dominant content of Si, Al and K presents at 75.95, 10.796 and 8.537 respectively comparable to the highest quality insulation materials.

ACKNOWLEDGEMENTS

The authors express their gratitude to gratefully acknowledge the support provided by Dr. Leonel Lira-Cortez from CENAM and Dr. Rodrigo Velázquez-Castillo from UAQ, for their technical support.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

AUTHORS' CONTRIBUTIONS

Author MGR designed the study, wrote the protocol, and wrote the first draft of the manuscript and managed the literature searches. Author MZG have completed the experiments. Both authors have read and approved the final manuscript.

REFERENCES

- [1] M. Galván-Ruiz and R. Velázquez-Castillo, "Cal, un antiguo material como una renovada opción para la construcción," *Ingeniería Investigación y Tecnología*, pp. XII, 1, 93-102. http://www.scielo.org.mx/scielo.php?script=sci_arttext&pid=S1405-77432011000100010&Ing=es&tIng=en, 2011.
- [2] C. Juárez, B. Guevara, P. Valdez and A. Durán-Herrera, "Mechanical properties of natural fibers reinforced sustainable masonry," *Construction and Building Materials*, pp. 24, 8, 1536-1541. <http://www.sciencedirect.com/science/article/pii/S0950061810000425>, 2010.
- [3] M. Galván-Ruiz, J. Hernández, L. Baños, J. Noriega and M. Rodríguez, "Characterization of Calcium Carbonate, Calcium Oxide, and Calcium Hydroxide as Starting Point to the Improvement of Lime for Their Use in Construction," *Journal of Materials in Civil Engineering*, pp. 694-698. DOI: 10.1061/(ASCE)0899-1561(2009)21:11(694), 2009.
- [4] D. Li and T. Lam, "An analysis of building energy performances and benefits using solar façades," *Journal of Power and Energy*, pp. 222, 3, 299-308. doi: 10.1243/09576509JPE404, 2008.
- [5] S. Jaber and S. Ajib, "Optimum, technical and energy efficiency design of residential building in Mediterranean region," *Energy and Buildings*, pp. 43, 8, 1829-1834. <http://www.sciencedirect.com/science/article/pii/S0378778811001022>, 2011.

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Not Highlight

Formatted: Font: Times New Roman, Not

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica, Spanish (Mexico)

Formatted: Font: Helvetica, Spanish (Mexico)

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

447 [6]—T.[5] D. Li and T. Lam, "An analysis of building energy performances and benefits using
 448 solar façades," *Journal of Power and Energy*, pp. 222,3, 299-308. doi:
 449 10.1243/09576509JPE404, 2008.

450

451 Uygunoğlu and A. Kecebas, "LCC analysis for energy saving in residential buildings with
 452 different types of construction masonry blocks," *Energy and Buildings*, pp. 43, 9, 2077-2085.
 453 <http://www.sciencedirect.com/science/article/pii/S0378778811001642>, 2011.

454

455 [7] H. Binici, O. Aksogan, M. Bodur, E. Akca and S. Kapur, "Thermal isolation and
 456 mechanical properties of fibre reinforced mud bricks as wall materials," *Construction and*
 457 *Building Materials*, pp. 21, 4, 901-906.
 458 <http://www.sciencedirect.com/science/article/pii/S0950061806000067>, 2007.

459

460 [8]—[6] T. Aslihan, "Thermal behavior of masonry walls in Istanbul," *Construction and*
 461 *Building Materials*, pp. 18, 2, 111-118. <http://dx.doi.org/10.1016/j.conbuildmat.2003.08.014>,
 462 2004.

463

464 [9][7] H. Kus, E. Özkan, Ö. Göcer y E. Edis, «Hot box measurements of pumice aggregate
 465 concrete hollow block walls.» *Construction and Building Materials*, vol. 38, pp. 837-845.
 466 <http://www.sciencedirect.com/science/article/pii/S0950061812007155>, 2013.

467 [8] T. Uygunoğlu and A. Kecebas, "LCC analysis for energy-saving in residential buildings
 468 with different types of construction masonry blocks," *Energy and Buildings*, pp. 43, 9, 2077-
 469 2085. <http://www.sciencedirect.com/science/article/pii/S0378778811001642>, 2011.

470

471 [9] H. Binici, O. Aksogan, M. Bodur, E. Akca and S. Kapur, "Thermal isolation and
 472 mechanical properties of fibre reinforced mud bricks as wall materials," *Construction and*
 473 *Building Materials*, pp. 21, 4, 901-906.
 474 <http://www.sciencedirect.com/science/article/pii/S0950061806000067>, 2007.

475

476 [10] B. Demirel, «Optimization of the composite brick composed of expanded polystyrene
 477 and pumice blocks.» *Construction and Building Materials*, vol. 40, pp. 306-313.
 478 <http://www.sciencedirect.com/science/article/pii/S0950061812008197>, 2013.

479

480 [11] R. Velázquez-Castillo, M. Pérez-Lara, E. Rivera-Muñoz, J. Arjona, M. Rodríguez-
 481 García, A. Acosta-Orsorio and M. Galván-Ruiz, "Thermal Imaging as a Non Destructive
 482 Testing Implemented in Heritage Conservation," *Journal of Geography and Geology*, pp. 4,
 483 4, 102-113. DOI: 10.5539/jgg.v4n4p102, 2012.

484

485 [10][12] A. Korjenic, V. Petráněk, J. Zach and J. Hroudová, "Development and performance
 486 evaluation of natural thermal-insulation materials composed of renewable resources," vol.
 487 43, no. 9, 2518-2523, 2011.

488

489 [11][13] P. Ihm and M. Krarti, "Design optimization of energy efficient residential buildings in
 490 Tunisia," *Building and Environment*, pp. 58, 81-90.
 491 <http://www.sciencedirect.com/science/article/pii/S0360132312001710>, 2012.

492

493 [12] I. Topcu, "Semi lightweight concretes produced by volcanic slags," *Cement and*
 494 *Concrete Research*, pp. 27, 1, 15-21.
 495 <http://www.sciencedirect.com/science/article/pii/S0008884696001901>, 1997.

496

497 [13] H. Wang and L. Wang, "Experimental study on static and dynamic mechanical
 498 properties of steel fiber reinforced lightweight aggregate concrete," *Construction and*

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

499 *Building Materials*, pp. 38, 1146-1151.

500 <http://www.sciencedirect.com/science/article/pii/S0950061812006782>, 2013.

501

502 [14] I. Villaseñor and E. Graham, "The use of volcanic materials for the manufacture of
503 pozzolanic plasters in the Maya lowlands: a preliminary report," *Journal of Archaeological*
504 *Science*, pp. 37, 6, 1339-1347. <http://dx.doi.org/10.1016/j.jas.2009.12.038>, 2010.

505

506 [1514] G. Villeda-Muñoz, A. Castañeda-Miranda, R. Pless, J. Vega-Durán and J. Pineda-
507 Piñón, "Clay-Brick Firing in a High-Temperature Solar Furnace," *Ingeniería Investigación y*
508 *Tecnología*, pp. XII, 4, 395-408.

509 [http://www.scielo.org.mx/scielo.php?script=sci_arttext&pid=S1405-](http://www.scielo.org.mx/scielo.php?script=sci_arttext&pid=S1405-77432011000400004&lng=es&nrm=iso)
510 [77432011000400004&lng=es&nrm=iso](http://www.scielo.org.mx/scielo.php?script=sci_arttext&pid=S1405-77432011000400004&lng=es&nrm=iso), 2011.

511

512 [1615] E. Yaşar and Y. Erdoğan, "Strength and thermal conductivity in lightweight building
513 materials," *Bulletin of Engineering Geology and the Environment*, pp. 67, 4, 513-519. doi
514 10.1007/s10064-008-0166-x, 2008.

515

516 [1716] R. Yao, Y. Yang and B. Li, "A holistic method to assess building energy efficiency
517 combining D-S theory and the evidential reasoning approach," *Energy Policy*, pp. 45, 277-
518 285. <http://www.sciencedirect.com/science/article/pii/S0301421512001498>, 2012.

519

520 [1817] N. Libre, M. Shekarchi, M. Mahoutian and P. Soroushian, "Mechanical properties of
521 hybrid fiber reinforced lightweight aggregate concrete made with natural pumice,"
522 *Construction and Building Materials*, pp. 25, 5, 2458-2464.

523 <http://www.sciencedirect.com/science/article/pii/S095006181000588X>, 2011.

524

525 [1918] P. Muñoz, M. Juárez, M. Morales and M. Mendiivil, "Improving the thermal
526 transmittance of single-brick walls built of clay bricks lightened with paper pulp," *Energy and*
527 *Buildings*, vol. 59, p. 71-180. <http://dx.doi.org/10.1016/j.enbuild.2013>.

528

529 [19] P. Ihm and M. Krarti, "Design optimization of energy efficient residential buildings in
530 Tunisia," *Building and Environment*, pp. 58, 81-90.

531 <http://www.sciencedirect.com/science/article/pii/S0360132312001710>, 2012.

532 [20] I. Topçu, "Semi lightweight concretes produced by volcanic slags," *Cement and*
533 *Concrete Research*, pp. 27, 1, 15-21.

534 <http://www.sciencedirect.com/science/article/pii/S0008884696001901>, 1997.

535

536 [21] H. Wang and L. Wang, "Experimental study on static and dynamic mechanical
537 properties of steel fiber reinforced lightweight aggregate concrete," *Construction and*
538 *Building Materials*, pp. 38, 1146-1151.

539 <http://www.sciencedirect.com/science/article/pii/S0950061812006782>, 2013.

540

541 [22] J. Yu, C. Yang, L. Tian and D. Liao, "A study on optimum insulation thicknesses of
542 external walls in hot summer and cold winter zone of China," *Applied Energy*, pp. 86, 11,
543 2520-2529. <http://www.sciencedirect.com/science/article/pii/S0306261909000841>, 2009.

544

545 [2023] OLADE, "Organización Latinoamericana de Energía. Informe de Estadísticas
546 Energéticas," 2009. [Online]. Available: <http://olade.org>. [Accessed 1 May 2013].

547

548 [24] American Society for Testing and Materials, ASTM C177: Standard Test Method for
549 Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of
550 the Guarded Hot-Plate Apparatus, ASTM. <http://archive.org/details/gov.law.astm.c177.2004>,
551 2004.

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573

[21][25] OLADE, "Organización Latinoamericana de Energía. Informe de Estadísticas Energéticas," 2009. [Online]. Available: <http://olade.org>. [Accessed 1 May 2013].

[22] American Society for Testing and Materials, *ASTM D 4927: Standard Test Methods for Elemental Analysis by Wavelength-Dispersive X-Ray Fluorescence Spectroscopy*, ASTM.

[23] B. Demirel, «Optimization of the composite brick composed of expanded polystyrene and pumice blocks,» *Construction and Building Materials*, vol. 40, pp. 306-313. <http://www.sciencedirect.com/science/article/pii/S0950061812008197>, 2013.

[24] H. Kus, E. Özkan, Ö. Göcer y E. Edis, «Hot box measurements of pumice aggregate concrete hollow block walls,» *Construction and Building Materials*, vol. 38, pp. 837-845. <http://www.sciencedirect.com/science/article/pii/S0950061812007155>, 2013.

[25][26] J. Shackelford, *Introduction to Materials Science for Engineers*, New York: Pearson, 2008.

1 ——— P. Muñoz, M. Juárez, M. Morales and M. Mendivil, "Improving the thermal transmittance of single brick walls built of clay bricks lightened with paper pulp," *Energy and Buildings*, vol. 59, p. 71-180. <http://dx.doi.org/10.1016/j.enbuild.>, 2013.

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Font: Helvetica

Formatted: Normal, Tab stops: Not at 0.28"

Page 3: [1] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [1] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [1] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [1] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [1] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [1] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [2] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [3] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [3] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [3] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		
Page 3: [3] Formatted	Miguel Galván Ruiz	5/24/2013 11:26:00 AM
Not Highlight		

[illegible]