

Research Paper

**EXTRACTION AND ANALYSIS OF CHEMO-PHYSICAL PROPERTIES OF YELLOW
OLEANDER OIL AS LUBRICANT.**

ABSTRACT

Yellow Oleander (*Thevetia Peruviana*) oil has been extracted and analyzed relevant to lubrication. Oil was extracted from yellow oleander seeds using mechanical expression and solvent extraction methods. Samples generated from these oils were subjected to chemo-physical analysis. Analysis of chemo-physical properties (such as viscosity, specific gravity, viscosity-temperature coefficient and fire point among others) was carried out using simple laboratory equipment. Results obtained showed that yellow oleander oil have properties that fall within the range of standard oil lubricants. High flash and fire points of 350°C and 375°C respectively were obtained. Free fatty acids content of 5.61% against a standard range of 35%-50% for natural oils. Specific gravity of 0.89-0.92 was obtained against a standard range of 0.76-0.92 for oil lubricants. The oil can be used as lubricant in environmentally sensitive areas such as total loss lubrication and marine ecosystems with associated positive environmental and economic impact.

Key words: [Analysis, chemo-physical, extraction, lubricant, oleander oil, properties].

Comment [X1]: Check this throughout the manuscript

Comment [X2]: Remove the brackets

1. INTRODUCTION

Growing environmental awareness, concerns of economic security and more stringent regulations regarding petroleum products have spurred renewed interest in natural oils as alternative lubricants. Three main types of oil lubricants are currently in use viz; mineral oil-based lubricants (also called mineral

36 oils) – derived from petroleum crude oil, synthetic lubricants and plant-based lubricants (or biodegradable
 37 natural oils). Mineral oils are predominantly in use. Synthetic lubricants are formulated to possess specific
 38 high performance properties. Plant-based lubricants are derived from naturally occurring oil seed.

39 This work seeks to analyze the chemo-physical properties of Yellow Oleander (*Thevetia Peruviana*) oil as
 40 alternative lubricant. The choice of Yellow Oleander oil was informed by its abundance and ease of
 41 cultivation of the oil crop in short rotation plantations.

Comment [X3]: ??? motivated?

42 The yellow oleander plant belongs to the family of plants called *Apocynaceae*. It is a small tree or shrub
 43 with yellow, bell-shaped flowers native to the Mediterranean regions of Southern Europe and South West
 44 Asia [1]. In Nigeria, it thrives in almost every part and it is grown in most parts of the country for
 45 horticultural purposes due to its beautiful flowering habit. Flowering occurs all year round with most
 46 profuse flowering occurring at warmer months. It is a fast growing crop and takes between one and three
 47 years to fruit. Transplants of oleander are easy from woody stem cutting. The fruit of the yellow oleander
 48 plant is trapezoidal in shape with fleshy green epicarp that turns black before dropping. and It has a hard
 49 brown nut which is also trapezoidal in shape, having two to four seeds in it. The seeds have high oil
 50 content. It is a tropical/tender perennial plant that grows up to a height of between 3-3.6m and blooms all
 51 year. The soil pH requirement for the plant is between the ranges 6.6-7.5 or 7.6-7.8 [2].

52 Yellow oleander oil can be extracted from the seeds by mechanical pressing and solvent extraction
 53 methods. Solvent extraction is employed in large scale operations for a more complete extraction than is
 54 possible with mechanical pressing using N-heptane, N-hexane, ethanol, etc.

55 Oils are evaluated for lubrication performance by determining their chemo-physical, thermal, frictional and
 56 rheological properties and characteristics. The chemo-physical properties include viscosity, viscosity
 57 Index, density, specific gravity, bulk modulus or compressibility, flash point, surface tension, oiliness,
 58 freezing point, fire point, cloud point, appearance/color, odor and water content. Recognition of these
 59 properties is useful for designing lubrication systems, choosing lubricating oils, diagnosing lubrication,
 60 friction and wear problems and also for selecting appropriate testing methods [3].

61 Sheanut, groundnut and palm kernel oils were worked on as alternative lubricants in upset forging[4].
 62 The extraction and saponification of rubber oil as well as the effect of processing conditions on the
 63 rheology of palm oil carried out [5,6]. The rheology of canarium oil and the rheology of palm, soy, rubber

Comment [X4]: Space

and gmelina oils as alternative lubricants were investigated [7,8]. The yellow oleander oil crop is not well established as a source of raw material for oil lubricant production. The basic quality parameters of palm oil (i.e. saponification values, iodine value, acid value, refractive index) varies with processing methods [9, 10]. Soy bean has high oil content fatty acids such as oleic acid, stearic acid, palmitic acid, linoleic acid among others [11]. Rubber seed oil contains fatty acids which endears it to the cosmetic and paint industries [5]. Although rubber seed oil viscosity is high, its odour is objectionable due to degradation and oxidation reactions of fatty acids, glycerides and other proteins in the raw oil [12]. Large quantities of Yellow Oleander (*Thevetia peruviana*) seeds are wasted annually on the ground in various parts of Nigeria. This work seeks to determine the suitability of yellow oleander oil as alternative machine lubricant by evaluating its chemo-physical properties, and establish the need for the cultivation of yellow oleander in commercial quantities.

75
76
77
78

2. METHODOLOGY

Yellow oleander fruits were picked from ornamental gardens around Makurdi town while the laboratory equipment were obtained in the food chemistry laboratory and Mechanical Engineering of the University of Agriculture, Makurdi.

2.1 Gravimetric Analysis of Oil Seeds

Fresh yellow oleander fruits were weighed using weighing scale (Denver instrument model XR1500) and the average weight was recorded. The fruits were left to undergo biodegradation for two weeks, after which the nuts were removed. The nuts were manually cracked to remove the oils seeds. The weights of the nuts and oil seeds were noted and their respective average weights were recorded.

The moisture content of the oil seeds was determined by drying a measured quantity of the seeds in electric oven (Genelab model B65) to constant weight at 105° C.

Moisture Content =
$$\frac{\text{Initial weight of oil seed} - \text{Final weight of oil seed}}{\text{Final weight of oil seed}} \text{----(1)}$$

The following ratios were determined using equations (2) to (4).

Fruit / oil seed ratio =
$$\frac{\text{Weight of fruit}}{\text{Weight of Oil seed}} \text{-----(2)}$$

Comment [X5]: Why different extraction methods? For what purposes?

$$\text{Nut / fruit ratio} = \frac{\text{Weight of Nut}}{\text{Weight of Fruit}} \text{-----}(3)$$

$$\text{Fruit / nut ratio} = \frac{\text{Weight of Fruit}}{\text{Weight of Nut}} \text{-----}(4)$$

In order to determine the oil / oil seed ratio, the measured portion of the oil seed was pulverized using grinding machine and oil was extracted using the solvent extraction method with ethanol as solvent. The oil / oil seed ratio was determined using equation (5).

$$\text{Oil / Oil seed ratio} = \frac{\text{Weight of Oil from Oil seeds}}{\text{Weight of Oil seeds}} \text{-----}(5)$$

2.2 Oil Extraction by Solvent Method

Oil was extracted from the oil seeds of yellow oleander using the solvent method [5, 13]. The mesocarp of yellow oleander nuts was manually cracked to remove the oil seeds. The oil seeds were dried to constant weight in the oven and the seeds pulverized into paste using a laboratory grinder. The paste was mixed with ethanol at 45°C over a hot plate (Stuart model) for one hour in a mass ratio of 0.9/0.1 (liquid/solid). The mixture was filtered with a sieve of 0.1µm mesh size to obtain a full miscella. The miscella was placed in a distillation column and then distilled at 110°C to obtain yellow oleander oil. The oil was dried in electric oven at 105°C for two hours to reduce the moisture content in the oil. The ethanol used was recovered up to 98% recovery.

Comment [X6]: What mass was used?

Comment [X7]: Temperature?

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Comment [X8]: Why didn't you use a non-polar solvent for the extraction? Usually, oils are non-polar compounds. Or did you have any idea about the polarity of the oils present in the extracts???

2.3 Oil Extraction by Mechanical Expression Method

Mechanical expression method was also used to extract yellow oleander oil [13]. Yellow oleander oil seeds dried to constant weight in the oven were ground into fine paste using a laboratory grinder. 50mg of boiling water (100°C) was added to a portion of the paste and thoroughly mixed. This mixture was poured into the remaining portion of the paste and thoroughly mixed at 60°C over a hot plate for an hour. The addition of boiled water was to agitate the oil in the oil matrix to ensure a high percentage of removal oil from the oil seeds. The paste was poured into a filter material with a mesh size of 0.1µm and squeezed in a laboratory hydraulic press gradually until the oil was drained from the oil seeds. The oil obtained was dried at 105°C for one and half hours in the electric oven to reduce moisture content of the oil. The oil was packaged into containers.

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

The samples were generated from one litre of the reference oil (Regal 32) and half a litre each of yellow oleander oil obtained from the two extraction methods as shown in Table 1.

2.4 Chemo-Physical Analysis

The following analyses were conducted on the oil samples: specific heat capacity, free fatty acids content, specific gravity, oil retention test, flash point, fire point, cloud point, pour point, foamability, foam stability, viscosity and viscosity – temperature coefficient. Specific heat capacity was determined as described in ASTM D3947 using differential calorimeter [14], free fatty acids content was determined as described by [15]. Specific gravity (ASTM D-1298), flash and fire points (ASTM D-92), oil retention, pour point (ASTM D-97) and viscosity (IP71/ASTM D-445) were determined [16]. Foamability and foam stability (ASTM D-892) and viscosity- temperature coefficient were determined [3, 17].

Comment [X9]: 1st mention in full!

Comment [X10]: 1st mention in full!

Table 1 -Straight and Blended Oils for Chemo-Physical Analysis

Sample	Regal 32	:	Yellow Oleander Oil
A ₁	1	:	0
A ₂	0	:	1
A ₃	1	:	10
A ₄	1	:	20
A ₅	1	:	30
B ₁	1	:	0
B ₂	0	:	1
B ₃	1	:	10
B ₄	1	:	20
B ₅	1	:	30

3. RESULTS AND DISCUSSION

3.1 Gravimetric Performance

Table 2 shows the results of the gravimetric analysis of yellow oleander seeds. In the table, four basic ratios were established for the oil seeds. These ratios were oil / oil seed ratio (0.02), oil seed / nut ratio (0.10), nut / fruit ratio (0.22) and oil seed / fruit ratio (0.02). These ratios facilitate the determination of oil yield from a given quantity of fruits. It is therefore, possible to determine the impact of oil produced on the upstream agricultural activities. In carrying out a feasibility study of production and materials requirement for lubricants production, these ratios play a predominant role. Thus, a knowledge of the quantity of fruit required for a given oil base stock, determined from these ratios would provide the upstream yellow oleander farmer with a knowledge of the farm size required. The oil / oil seed ratio obtained was lower than oil / oil seed ratio obtained for gmelina oil seed (0.16) and rubber oil seed (0.08) [18]. Therefore, for a given quantity of yellow oleander, gmelina and rubber oil seeds, oil yield are expected to be lowest in yellow oleander oilseeds. However, oilseed / nut ratio of 0.10 obtained in this work, gives a lower waste generation during the actual lubricant production.

Table 2: Gravimetric Analysis of Yellow Oleander Oil Seeds

Items	Values
Average Weight of Fruit (Fresh), g	18.85
Average Weight of Nut, g	4.19
Average Weight of Oilseed, g	0.40
Moisture Content in Oilseed, %	2.73
Percentage of Oil in One Oilseed, %	21.3
Fruit to Oilseed ratio	0.02
Nut to Oilseed ratio	0.10
Fruit to Nut ratio	0.22
Oil to Oilseed ratio	0.02

3.2 Chemo-Physical Analysis

In Tables 3 and 4, the chemo-physical properties of oil samples are shown. Table 3, shows the chemo-physical properties of oil samples obtained by mechanical expression. In the table, the odor of yellow oleander oil, the reference oil and the blends were mild. This was contrary to the findings of [5] for rubber seed oil, whose use was discontinued at Delta Steel Complex, Aladja, Nigeria due to offensive odor. Yellow oleander oil obtained by solvent extraction method was also found to have mild odor. The use of yellow oleander oil and its blends as lubricants will be conducive to workers on the basis of odor.

The specific gravity of yellow oleander oil and the blends in Table 3 fell within the range of 0.906 and 0.912, while in Table 4, the specific gravity fell between 0.84 and 0.89 for the oil extracted by solvent extraction. The specific gravity fell within the standard range of 0.76-0.92 for oil lubricants [3]. The disparity between the specific gravity of oil samples obtained was possibly due to loss of wax from the solvent extracted oil arising from heat input during extraction. The disparity in specific gravity between the reference oil and yellow oleander oil and the blends was possibly due to the processing undergone by the reference oil.

The cloud points of yellow oleander oil and its blends in Tables 3 and 4 fell within the range of 6°C and 9°C and the pour points for yellow oleander oil fall between the range of 4°C and 7°C respectively. However, it was observed by [3] that the lower the cloud and pour point of oils, the better the pumping property at start-up of engines at relatively low temperatures. The reference oil had relatively lower pour and cloud points than the yellow oleander oil and its blends possibly due to absence of wax and other contaminants. Compared to some natural oils such as gmelina, rubber, palm, soy, ground nut, shear butter and wild melon oils, the pour point of yellow oleander is very good and can easily be improved by treatment [4, 18, 19].

Natural oils generally have high flash and fire points which make them very safe as lubricants in fire-prone operations [20]. The flash and fire points obtained for yellow oleander and its blends as shown in Tables 3 and 4 were exceptionally higher than the reference oil. The flash point of yellow oleander oil was high when compared with rubber seed oil, wild melon oil, palm oil and gmelina oil [4, 18]. Industrial fire is a serious hazard often encountered in lubrication where accidental increases in temperature are

Comment [X11]: Insert the name and year followed by the reference number. Also check throughout the manuscript!

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Comment [X12]: Specify kind of treatment

encountered due to acts of negligence. Under this condition, oils with high flash and fire points will prove invaluable. The high flash and fire points for yellow oleander oil would provide safe machine lubrication. The ability of oil to remain in the bearing after application determines to a large extent the functional stability of that oil. Yellow oleander oils retention property was higher than that of the reference oil as shown in Tables 3 and 4. This was because yellow oleander contained more wax than the reference oil. In machine lubrication, the apparent good retention property of yellow oleander oil would be eroded when the machine attains its operating speed, as a result of melting of the wax material in the oil. However, in boundary lubrication this oil retention property enhances the adsorptive behavior of the oil. The percentage retention of yellow oleander oil (40.51%) was observed to be higher than that of rubber seed oil (7.69%), gmelina oil (9.42%), palm oil (33.19%) and soy oil (3.52%) [18]. The difference in oil retention can be attributed to differential molecular affinity between the various natural oils and solid boundaries.

Table 3: Chemo-Physical Properties of Oil Samples from Mechanical Pressing

	A ₁	A ₂	A ₃	A ₄	A ₅
Odor	Mild	Mild	Mild	Mild	Mild
Color	Yellowish Brown	Light Yellow	Deep Yellow	Mild Yellow	Mild Yellow
Specific Gravity	0.870	0.912	0.906	0.909	0.909
Density, kg/m³	870	912	906	909	909
°API	31.14	23.65	24.68	24.17	24.17
Cloud Point, °C	-5.5	9	8	7.5	7.5
Pour Point, °C	<-10	7	6.5	5	4.5
Flash Point, °C	180	350	280	290	320
Fire Point, °C	200	375	310	318	345
Oil Retention, %	12.40	40.05	15.12	8.32	22.57
pH	6.18	5.83	4.91	4.76	4.15

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Specific Heat Capacity, J/kg k ⁻¹	19500	6720.05	6756.30	4998.42	4410.02
Free Fatty Acids, %	1.96	5.61	4.49	5.05	5.19
Viscosity at 40°C, cSt	64.57	78.97	84.49	78.71	75.03
Viscosity at 70°C, cSt	48.43	50.36	72.83	67.46	57.72
Viscosity at 100°C, cSt	32.24	39.42	44.75	52.47	40.24
Viscosity-Temperature Coefficient	0.50	0.50	0.47	0.33	0.46

Comment [X13]: ???

Formatted: Highlight

Comment [X14]: ???

Formatted: Highlight

Comment [X15]: ???

Formatted: Highlight

Table 4:Chemo-Physical Properties of Oil Samples from Solvent Extraction

	B ₁	B ₂	B ₃	B ₄	B ₅
Odor	Mild	Mild	Mild	Mild	Mild
Color	Yellowish Brown	Light Yellow	Deep Yellow	Mild Yellow	Mild Yellow
Specific Gravity	0.85	0.89	0.84	0.88	0.88
Density, kg/m ³	850	890	840	880	880
°API	34.99	27.49	36.95	29.30	29.30
Cloud Point, °C	-7	9.0	7.0	7.5	80
Pour Point, °C	<-10	6.0	5.5	5.0	4.5
Flash Point, °C	180	352	280	291	320
Fire Point, °C	200	374	305	320	349
Oil Retention, %	12.38	40.51	15.19	7.69	22.57
pH	6.18	5.90	4.99	4.85	4.10

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

Specific Heat Capacity, J/kg k⁻¹	19500	6726.3	6888.6	5000	4437.7
Free Fatty Acids	1.98	5.23	4.37	5.00	5.20
Viscosity at 40°C, cSt	62.10	75.66	82.69	75.04	74.15
Viscosity at 70°C, cSt	46.30	56.36	68.31	67.09	57.68
Viscosity at 100°C, cSt	31.18	39.08	40.63	52.53	39.95
Viscosity-Temperature Coefficient	0.50	0.48	0.51	0.30	0.46

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

243
244
245
246

247

248

249 The pH values of the yellow oleander oil and its blends in Tables 3 and 4 fall within the ranges of 4.15 -
250 5.83 and 4.10 – 5.90. It was observed that the pH values in Tables 3 and 4 are lower than that of the
251 reference oil which was an indication that they are more acidic than the reference oil. The acidity of oil
252 provides a reference point for monitoring oil condition during use. An increase in acidity of oil during use
253 as a lubricant shows the accumulation of oxidation products in the oil. This is therefore a primary factor in
254 condition-based maintenance of engineering mechanisms.

255 The specific heat capacity of the oil samples is as shown in Tables 3 and 4. The specific heat capacity of
256 the reference oil (19500J/kgk⁻¹) was higher than that of yellow oleander oil and its blends. This was
257 because the reference oil has undergone processing to enable it perform specific industrial lubrication
258 functions. Addition of yellow oleander oil to the reference oil gave rise to a progressive decrease in the
259 specific heat capacity of the blends which was lowest at A₅ (4410.02J/kgk⁻¹) and B₅ (4437.70J/kgk⁻¹). The
260 specific heat capacity of oil determines the amount of heat the oil can tolerate in actual service before
261 deterioration sets in. In hydrodynamic lubrication, specific heat capacity is used in the determination of
262 heat transfer, temperature rise and other thermal factors in oil [3].

263 Free fatty acids for natural oils fall within a range of values normally higher than that of mineral base oils
264 [4, 19]. High values of percentage free fatty acids obtained for yellow oleander and other natural oil such
265 as gmelina oil (37.49%), rubber oil (50.33%) and palm oil (39.47%) stands them out as good boundary
266 lubricants [18]. This is due to formation of metallic soaps between surfaces in contact with the oil [17].

Viscosity is by far the most significant property for establishing the thickness, pressure and temperature of an oil in hydrodynamic and elastohydrodynamic lubrication [3]. The viscosities obtained for the oil samples shown in Tables 3 and 4 fell within the range of 84.48 cSt at 40°C and 32.24 cSt at 100°C for both types of oil samples. The viscosity of yellow oleander oil was within the range of standard oil lubricants (60cSt at 40°C and 24cSt at 100°C) and can be upgraded to obtain function-specific viscosities. The lower the viscosity-temperature coefficient, the higher the viscosity index of oil. Viscosity-temperature coefficient, an indication of the change in viscosities with temperature for the oil samples is shown in Tables 3 and 4. The difference between values shown in Tables 3 and 4 may be attributed to the different extraction processes. The values obtained for the yellow oleander oil and its blends compare favorably with results obtained for the reference oil. It was observed that the viscosity-temperature coefficient obtained with the two extraction methods were approximately the same (0.50). Therefore, processing methods of yellow oleander oil does not seem to affect the viscosity-temperature coefficient [18].

Formatted: Highlight

Formatted: Highlight

Formatted: Highlight

279

280

281

282

283 4. CONCLUSION

Oil was extracted from yellow oleander seeds and evaluated for lubrication performance. The extraction methods used did not affect the chemo-physical properties obtained for the oil. The functional properties obtained experimentally in this work for yellow oleander oil is within the range of standard oil lubricants. Yellow oleander has a remarkably high flash and fire points. The viscosity and flash points of the oil are adequate for application as a hydrodynamic oil lubricant in actual service. It can therefore be considered for use in transmission and gear train lubrication. It may also be used for lubrication of rollers, cams and journal bearings. On account of its fire point, low free fatty acids, specific heat capacity and pour point, it can be used as a hydraulic, brake and transformer oils. The oil has high oil retention property which makes it suitable for use in sealed ball and roller bearings in low-medium load applications. When

upgraded, this oil may be used for high load ball and roller bearings. This, like other natural oils is suitable for marine applications as it is environment-friendly and biodegradable

295

COMPETING INTERESTS

No competing interests exist.

AUTHORS' CONTRIBUTIONS

Author A identified the problem, set the objectives, designed the methodology and supervised the entire project work. Authors A, B and C reviewed the relevant literature. Authors' B and C collected materials for the analysis while the analysis was done by Authors A, B and C. The draft manuscript was produced by Authors B and C while Author A did the final review ~~that as~~ was agreed ~~on~~ by ~~all the~~ three Authors.

303

REFERENCES

1. Gilman, E and Watson, D. " *Nerium Oleander – Oleander*" (*Fact sheet ST-412*). Gainesville, _____Florida, 1994.
2. Pagen, FJJ. "Oleanders- *Nerium L.* and the Oleander Cultivars". Netherlands Agricultural University. 1988.
3. Herguth, _____HR, and Godfrey D. "Physical and Chemical Properties of Mineral Oils that affect Lubrication", Herguth Laboratories Inc, Vallejo, Ca, 1995.
4. Oyinola, AK. "Determination of performance Characteristics of Local Oils as Lubricants" *Nigeria J. of Engineering*. 2 (1). 1984, 40-47.
5. Onukwuli, OD, Okeke, SI, Agbo, GU, Ekumankama, EO and Udeobi, OO, _____ "Extraction, Deodorization and Saponification of Rubber Seed Oil". *NSE Transactions* 35 (1), 2000, 5-11.
6. Satimehin, AA, Akinremi, OM And .Ijabo, OJ. "Rheological behavior of palm oil" *Science Forum: Journal of Pure And Applied Sciences*. Vol. 6 No. 2, 2003, 291-297.
7. Alakali, JS, Ijabo, OJ and Satimehin, AA. "Rheological Characteristics of Canarium (*Canarium Schweinfurhii*) Oil", *Science Forum, Journal of Pure and Applied Sciences*, 2 (6), 2003, 298-303.
8. Oseni, MI, Nnuka, EE and Ette, AO. "Rheological Behavior of Selected Natural Oils as Alternative Lubricants", *J. of Metallurgy and Materials Engineering*, 2(1), 2005, 27-_____33.
9. Oshinowo, T, _____ "Evaluation of some Nigerian Oils as Potential Raw Materials for Polyvinyl Chloride Thermal Stabilizers", *J.I. of Nigerian Society of Chemical Engineers*, 6(1), 1987, 36-41.

Comment [X16]: Please redo the reference. Will look much better with recent references!

Formatted: Highlight

- 327 10. Adeosun, BF, Olaofe, O and Ajayi, JD. "Evaluation of the Nigerian Traditional Soap as a
328 Processing Aid in Natural Rubber Vulcanization". *J. of Technoscience*. Vol. 4, 2000, 5.
- 329 11. Bishop, DG, Carter, LP, Chapman, SR and Benett, WF. "Crop Science and Food Production",
330 New York, Mc Graw Hill Book Company. 1983, 231-245.
- 331 12. Achinewhu, SC. "Unconventional Sources of Food ; Chemical Composition of Rubber Seed
332 (Hevea Brasiliensis)" Food Chemistry, 1986, 21.
- 333 13. McCabe, WL, Smith, JC and Harriott, P. "Unit Operations in Chemical Engineering" 4 edn,
334 New York, McGraw-Hill book company, 1985.
- 335 14. Mohsenin, NN. "Thermal properties of foods and agricultural materials" New York, Gordon
336 and Breach Science Publishers, 1980.
- 337 15. David, P. "The Chemical Analysis of Food". 6 edn. London, J. A Churchill, 1970.
- 338 16. Baker, AE. "Lubricant Properties and Test Methods Handbook of Lubrication, Theory and
339 Practice of Tribology," Vol. I, Ed. E. R. Booser, CRC Press, 1984.
- 340 17. Fuller, DD. "Theory and practice for lubrication Engineers" 2 edn. Wiley and Sons, New York.
341 1984.
- 342 18. Oseni, MI, Nnuka, EE and Ette, AO. "Evaluation of Chemo-Physical Properties of
343 Selected Natural Oils Relevant to Lubrication", *Nigerian J. of Engineering Research and
344 Development*, 5(2), 2006, 1-9.
- 345 19. Hartley, CWS. "The Oil Palm", 3 edn, Tropical Agricultural Sciences, New York,
346 Longman Scientific and Technical Publications, 1988.
- 347 20. Nelson, J. "Harvesting Lubricants" *The Carbohydrate Economy*. Vol. 3 No.1, 2000, 12.