

Biodiesel Production from Tigernut (*Cyperus esculentus*) Oil and Characterization of its Blend with Petro-diesel

Ofoefule, A.U^{*1}., Ibeto, C.N¹., Okoro, U.C² and Onukwuli, O.D³

¹National Centre for Energy Research and Development, University of Nigeria, Nsukka.

² Department of Pure and Industrial Chemistry, University of Nigeria Nsukka, Enugu state.

³Department of Chemical Engineering, Nnamdi Azikiwe University Awka, Anambara state

ABSTRACT (ARIAL, BOLD, 11 FONT, LEFT ALIGNED, CAPS)

This study was carried out to assess the fuel quality of biodiesel produced from tigernut (*Cyperus esculentus*) oil and its blends with petro- diesel. The oil was extracted from the tigernut by solvent extraction method using petroleum ether. The oil was trans-esterified using potassium methoxide as a catalyst at the temperature of 60°C for 60 min using a catalyst concentration of 0.65% and under a constant stirring speed. The crude biodiesel obtained was purified by washing with water and subsequently dried in an oven. The biodiesel was again blended with petro- diesel to obtain various blends of B10, B20, B30 and B40. Oil and biodiesel yields were assessed while physicochemical analysis of the oil, biodiesel and blends were carried out using standard methods for physicochemical parameters including flash point, cloud point and pour point. Results obtained showed that the oil yield from the feedstock was 16%, while the biodiesel yield was 82%. Their high and moderate flash points ranged between 90-178°C, their cloud points ranged between 6.5-13°C while their pour points ranged between -3-(-10)°C. General results of the blends showed that B10 and B20 had performance results closer to B100, petro-diesel and ASTM standards. Therefore, the blends will be suited to engines not specifically designed for biodiesel use.

Keywords: Tigernut, transesterification, biodiesel, biodiesel blends, petro-diesel

1. INTRODUCTION

Currently there is a strong interest in biodiesel, mainly driven by growing volatility in global crude oil markets and concerns over climate change and the desire to address the global

*Corresponding Author

E-mail: akuzuoo@yahoo.com

Tel: +234-8036798570

24 risk. Biodiesel had proven to be a good substitute for petroleum diesel in motor vehicles and
25 generators, when it meets the international standards such as ASTM for automotive use.
26 Biodiesel is biodegradable, non-toxic and has low emission profiles when compared to fossil
27 fuel and its usage will allow balance between agriculture, economic development and the
28 environment [1]. Biodiesel is produced through a chemical process known as trans-
29 esterification. Transesterification of vegetable oils with low molecular weight simple alcohols
30 (methanol, ethanol, propanol, butanol and amyl alcohol) has been established as the best
31 option to reduce the high viscosity, low volatility, heavy engine deposits and toxic substance
32 formation associated with the direct use of vegetable oils [2, 3]. Tigernut is not really a nut
33 but a small tuber that was discovered some 4000 years ago. It has been cultivated both as
34 live stock food and for human consumption. It is widely grown in Florida, Spain, Britain,
35 China, Mali and Ivory Coast. The plant is widely distributed in West Africa where it is
36 cultivated mainly for the edible tubers which it bears underground. In northern Nigeria, the
37 tubers of Tigernut can be bought in the market all year round. The fatty acid composition is
38 mainly Oleic (75.72%), linoleic (11.64%) and Palmitic (10.21%) with traces of stearic,
39 Linolenic and Arachidic acids [4].

40 Many research works have exploited commercially edible oils like cotton seed oil, sun flower
41 seed oil, soy bean oil, peanut oil, coconut oil and palm oil as the feedstock for biodiesel [5,
42 6]. However availability of these raw materials varies. Although tigernut oil is from an edible
43 feedstock, its use as a potential feedstock for biodiesel production may not likely compete
44 with its use as food since it is not a staple food or widely consumed. Most parts of the tropics
45 are suitable for biofuels crop cultivation including tigernut. This strategy is effectively being
46 employed in USA and Brazil as they are the world largest producers of bioethanol from
47 Sugarcane and other raw materials [7]. Currently, tigernut use in Nigeria is mainly for
48 production of milk and as snacks etc. However, the tuber can be used for numerous
49 purposes aside from food consumption. It has been reported to effectively serve as a
50 supplementary feedstock for biodiesel production [8]. The high fibre content makes it useful
51 for pyrolysis / gasification to biofuels, the moderate starch content also makes it a potential
52 supplementary feedstock for bioethanol production [9]. The wastes emanating from its
53 processing also makes it a veritable feedstock for biogas production under anaerobic
54 digestion [9].

55 Some studies have been carried out on biodiesel production from Tigernut. Barminas *et al.*,
56 [10], carried out preliminary studies of transesterification of tigernut (*Cyperus esculentus*) as
57 a source of biofuel. Also, Ugheoke *et al.*, [8] studied the optimization of the transesterification
58 process of tigernut oil for biodiesel production, specifically to determine the optimal catalyst
59 concentration level that gives maximum yield of methyl ester (biodiesel) from the oil.

However, taking U.S as a case study, biodiesel is mostly blended with diesel fuel. Such a blend would have better cold flow properties when compared with neat biodiesel. Consequently, blending biodiesel with petrodiesel may be advantageous for mitigating the poor cold flow properties of biodiesel from many lipid feedstocks. On the other hand, blending at higher ratios may compromise cold flow properties [11]. Again, biodiesel contains no petroleum, but it can be blended with petroleum diesel in any percentage. Biodiesel blends from 2 percent to 20 percent can be used in most diesel equipment with minor or no modifications. This study was therefore undertaken to assess the fuel quality of biodiesel produced from methyl esters of tigernut (*Cyperus esculentus*) and its blends with petrol-diesel, in order to determine the most suitable blending ratio for biodiesel produced from tigernut seed oil with petro-diesel and also determine if higher blending ratios differ considerably in quality from lower blending ratios.

2. MATERIAL AND METHODS

2.1. Materials

Fresh tigernut was purchased from a local market in Enugu town of Enugu State, Nigeria. Analytical grade reagents were used for all the analyses carried out without further purification. The petroleum ether was used as procured without further purification. The Methanol used was a product of Merck, Darmstadt, Germany (99.7% purity), while the potassium hydroxide was a product of Loba Chemie GmbH Switzerland (85% purity). Other materials also used were fractionating column, aluminium foil, 1 liter beakers, 1 liter biodiesel reactor, thermo- regulator heater equipped with stirrer (Heizung Chauffage, MGW- LAUDA, D6970, Lauda- Königshofen, Germany), electronic digital weighing balance (Ohaus, Adventurer, model- AR 3130), specific gravity bottle, pH meter (Hanna pH meter model No. 02895), Rotary evaporator, oven (BTOV 1423), Vecstar furnace LF3, Ferranti portable viscometer model VL, Abbe refractometer, semi automatic Cleveland flash point tester and Hewlett Adiabatic Bomb Calorimeter model 1242. The study was carried out in the National Centre for Energy Research and Development, University of Nigeria Nsukka in August, 2010.

2.2. Oil extraction

The tigernut was washed with water and dried by sun drying. The seeds were ground into coarse particle sizes with a mechanical grinder (local mill) and placed in a solar dryer for four days to remove residual moisture. The dried meal was packed in a big fractionating column up to three quarter level and petroleum ether was poured well above the level of the meal in the column. It was closed with aluminium foil and masking tape and then left overnight. The

mixture of oil and solvent was collected from the bottom of the column with a beaker. This was repeated several times until all the oil from the meal has been extracted. The oil was recovered using rotary evaporator to distil off the solvents. After the distillation, the oil was left in the open to totally dry up.

2.3. Characterization of oil

The oil was characterized for pH using a pH meter, specific gravity using a specific gravity bottle, moisture content by the oven dry method, ash content by heating to dryness in furnace, kinematic viscosity using a viscometer, the acid value, saponification value, Iodine value and Peroxide value by titrimetry, refractive index using Abbe refractometer [12] and percentage free fatty acid (% FFA) (as oleic) was determined by multiplying the acid value with the factor 0.503. Thus % FFA = 0.503 x acid value [13].

2.4. Preparation of Potassium Methoxide

250 ml of methanol was measured into a 500 ml flat bottom flask and covered immediately. 5.8 g of potassium hydroxide was carefully added into the methanol to make a solution which was made airtight. It was shaken and swirled for a few times until the KOH was completely dissolved. This gave a catalyst concentration of 0.65%.

2.5. Biodiesel production and purification

The transesterification reaction was carried out in a 1 liter airtight biodiesel reactor vessel fitted with thermo-regulator heater/ stirrer. One litre of tigernut oil was measured into the flask and was heated to a temperature of 60°C. The potassium methoxide was then poured into the flask containing the oil and was immediately covered. The temperature of the system was maintained at 55-60°C for the one hour duration of the reaction. At the end of the reaction, the mixture was transferred into a separatory flask, left for 24 h and then the biodiesel separated from the glycerol by gravity. The biodiesel was purified by washing with water five times to obtain a clear water and neutral pH [14, 15]. The glycerol was not refined further but was kept for other uses.

2.6. Characterization of biodiesel and its blend

The different blends; B10, B20, B30 and B40 were prepared by mixing 10, 20, 30 and 40 ml biodiesel and 90, 80, 70, 60 ml petro-diesel respectively. They were analysed in the same way as the tigernut oil for the same parameters and also calorific value using a Bomb calorimeter, flash point using a semi automatic Cleveland flash point tester (ASTM D93), cloud point (ASTM D2500) and pour point (ASTM D97).

3. RESULTS AND DISCUSSION

Table 1 shows the proximate composition of the tigernut tuber and starch after de-oiling of the feedstock, while Table 2 shows the physicochemical properties of the tigernut oil. The calorific value, carbohydrate content and fat content of the tuber indicate that the feedstock would serve as a good source for biofuels production.

Table 1: Proximate composition of Tigernut tuber and starch

Parameters	Tigernut tuber	Tigernut starch
Moisture (%)	5.77	8.13
Ash (%)	1.86	6.14
Crude fibre (%)	9.50	7.98
Crude fat (%)	25.70	2.33
Crude protein (%)	7.00	3.24
Carbohydrate (%)	65.50	65.18
Calorific value(kcal/g)	524.60	345.88

As shown in Table 2, the oil yield from the tigernut was 16% which is quite low when compared with most oil seed feedstock. However, by-product of the nuts after extraction can be put to good use as feedstock for other biofuels production/application. The odour and clear golden yellow colour of the oil are favourable for biodiesel production.

Table 2: Physico-chemical properties of tigernut oil

Parameters	Results
Oil content (%)	15.91
Odour	Odourless
Colour	Yellow
Specific gravity	0.91
pH	5.30
Moisture (%)	5.32
Ash content (%)	2.60
Iodine value (g/100g)	143.37
Acid value (mgKOH/g)	8.97
Saponification value (mgKOH/g)	161.54
Peroxide value (mEq/Kg)	8.33
Free fatty acid (%)	4.49
Viscosity (mm ² /s)	0.98
Refractive index	0.77

Acid values of the oil and biodiesel were very high and exceeded the ASTM standard of 0.8 mgKOH/g (Table 3). Vegetable oils containing high free fatty acids have significant effects on the transesterification with methanol using alkaline catalyst. It also interferes with the separation of fatty acid ester and glycerols [16]. This also may have affected the yield of

biodiesel which was lower than most high yielding ones (95% and above). Even though it was lower than more favourable yield of 95% and above, it was however higher than that obtained for peanut oil reported by Itodo *et al.*, [17] and Ibeto *et al.*, [7]. This shows that the tigernut is not only a good feedstock for biodiesel production, but it also favours the single stage transesterification process. Therefore the cultivation of the crop should be encouraged in the tropics since it is not a staple food and would not interfere with food availability.

The specific gravities of the B100 and the blends were within the range and compared with that of biodiesel from other oil sources. Densities and other gravities are important parameters for diesel fuel injection systems. The values must be maintained within tolerable limits to allow optimal air to fuel injection systems.

Table 3: Physicochemical properties of petro-diesel, biodiesel and biodiesel blends

Parameters	Petro diesel	B100	B10	B20	B30	B40	ASTM Std
Biodiesel yield (%)	-	82					≥ 95
Specific gravity	0.85	0.87	0.86	0.86	0.85	0.85	0.875-0.90
Ash content (%)	-	1.13	1.53	1.53	1.20	2.0	0.01 max
Iodine value (g/100g)	-	98.38	90.35	90.35	90.46	90.46	120 max
Acid value (mgKOH/g)	-	1.122	1.683	1.724	2.805	2.68	0.05 max
Saponification value (mgKOH/g)	-	108.46	106.74	106.73	104.49	103.37	
Free fatty acid (%)	-	0.56	0.84	0.86	1.40	1.34	
Viscosity (mm ² /s)	5.51	8.08	4.54	4.71	4.84	5.68	1.9-6.0
Refractive index	-	0.77	0.86	0.75	0.77	0.86	
Calorific value (J/g)	22,905	-	15,140	26,851.	32,545	19,736	
Flash point (°C)	-	178	120	110	92	90	120 min.
Cloud point (°C)	-	13	11	9	6.5	8.0	
Pour point (°C)	-	-3	-7	-9	-10	-9	-10

The ash content of both the B100 and the blends were well above the standard. This indicates that it may likely have higher mineral contents leading to some level of air pollutants like SO_x and NO_x.

The viscosity of the B100 was slightly higher than the standard. However, the blends fell within the range required for use in the engines. They also compared well with the petro diesel whose viscosity was 5.51mm²/s. However, B10 and B20 had lower values than the other blends. The iodine values were within standard. Higher iodine values indicate high unsaturation in oils and fats. The values obtained in the B100 and blends showed that the unsaturation was taken care of by transesterification. There was no reasonable difference

between the values obtained for the different blends. Saponification value is used for checking adulteration. The saponification value for the B100 and the blends were lower when compared with that obtained for peanut oil (244.74 and 218.09 mg/KOHg⁻¹) and the Jatropha oil seed which was 193.55mgKOHg⁻¹ as reported by Akbar *et al.*, [18]. This indicates that the level of adulteration in the Tigernut oil biodiesel was very low.

The flash point of the B100 and blends except B40 were actually within the ASTM 6751 standard specification of 93°C set in order for the biodiesel to be classified as a non-hazardous material for shipping in the United States. This indicates that with their use, the fear of fire outbreaks would be eliminated. The value of the flash point for B30 and B40 indicate that they may not be very good blends for use. The cloud point and the pour point of both the B100 and the blends were well within the standard range. One of the problems associated with biodiesel is its cold flow properties represented by the pour point. The pour point is the lowest temperature at which frozen oil can flow and is used to specify the cold temperature instability of fuel oil. This shows that biodiesel from tigernut oil would perform very well in very cold and temperate regions. This also indicates that countries in the tropics where cultivation of tigernut thrives, can exploit this outlet into biofuels crop cultivation in order to export the oil to western countries for the purposes of biofuels production. They all also showed high calorific values. This indicates that they would burn with high release of energy.

4. CONCLUSION

The study has shown that tigernut is a very good feedstock for biodiesel production. The results of the blends of the petro-diesel with tigernut biodiesel showed that that B10 and B20 had results closer to B100 and to the ASTM standards and would give better performance than B30 and B40. Therefore, the blends will be suited to engines not specifically designed for biodiesel use. This compares very well with biodiesel from other oil sources. Even though tigernut oil is edible oil, the crop is not consumed on a large scale as a staple food and it is not also a major source of edible oil, so it would be advisable if countries in the tropics consider the cultivation of this crop on a large scale. If this is achieved, it would facilitate the use of tigernut for biodiesel production on a large scale and hence alleviate the global concern for food security.

AUTHORS' CONTRIBUTIONS

The first and corresponding author designed the study and wrote the protocol. Author 1 carried out the experimental studies. Author 2' wrote the first draft of the manuscript. 'Author

1' and 2' managed the analyses of the study while Authors 3' and 4' supervised the overall work. All authors approved the final manuscript."

REFERENCES

- [1] Meher LC, Sagar DV, Naik SN. Technical Aspect of Biodiesel Production by Transesterification- A Review. *Renewable Sustainable Energy Rev.* 3; 2004.
- [2] Schwab AW, Baghy MO, Freedman B. Preparation and properties of Diesel fuel from vegetable oils. *Fuel*, 1987; 66: 1372 – 1378.
- [3] Tesser R, Di Serio M, Guida M, Nastasi M, Santacesaria E. Kinetics of Oleic acid etherification with methanol in the presence of Triglycerides. *Ind. Eng. Chem. Res.*, 2005; 44: 7978- 7982.
- [4] Temple VJ. Lesser Known Plant Foods. In: Nutritional quality of plant foods A. U. Osagie and O. U. Eka (Eds.) Post harvest Research Unit, Department of Biochemistry, University of Benin. Benin City. Nigeria, 1998.
- [5] Syam AM, Yunus R, Ghazi TIM. Yaw TCS. Methanolysis of jatropha oil in the presence of potassium hydroxide catalyst. *J. Applied Sci.*, 2009; 9: 3161-3165.
- [6] Ofoefule AU, Ibeto CN, Ugwu LC, Eze DC. Determination of Optimum Reaction Temperature and Reaction Time for Biodiesel yield from Coconut (*Cocos nucifera*) oil. In proc. International workshop on Renewable Energy for sustainable Development in Africa (IWRESDA). Nondon Hotel, Enugu. 5th – 7th November, 2012.
- [7] Ibeto CN, Ofoefule AU, Ezeugwu HC. Fuel Quality Assessment of Biodiesel Produced from Groundnut Oil (*Arachis hypogea*) and its blend with petroleum diesel. *Amer. J. Food Tech.* 2011 6(9): 798-803.
- [8] Ugheoke BI, Patrick DO, Kefas, HM, Onche EO. Determination of Optimal Catalyst Concentration for Maximum Biodiesel Yield from Tigernut (*Cyperus esculentus*) Oil. *Leonardo Journal of Sciences*, 2007; 6(10): 131 - 136.
- [9] Ofoefule AU. Biofuels potentials of some biomass feedstock for bioethanol and biogas. PhD Thesis. University of Nigeria, Nsukka. 2012.
- [10] Barminas JT, Maina HM, Tahir S, Kubmarawa D, Tsware K. A preliminary investigation into the biofuel characteristics of tigernut (*Cyperus esculentus*). *Bioresour. Technol.*, 2001; 79: 87-89.
- [11] Dunn RO. Improving the Cold Flow Properties of Biodiesel by Fractionation, Soybean - Applications and Technology, Tzi-Bun Ng (Ed.), ISBN: 978-953-307-207-4, InTech, Available from: <http://www.intechopen.com/books/soybean-applications-and-technology/improving-the-cold-flow-properties-of-biodiesel-by-fractionation>. Accessed 13/11/2012
- [12] Van Gerpen JH. Biodiesel processing and production. *Fuel Processing Technology*, 2005; 86 (10): 1097–1107.

- 265 [13] Ejilah IR, Asere AA. Tested performance parameters of Transesterified sheanut oil and
266 diesel fuel blends in compression ignition engines. In proc. National Solar Energy Forum
267 (NASEF). University of Agriculture, Makurdi. Benue state. 2010: 1-14.
268
- 269 [14] Alamu OJ, Waheed MA, Jekayinfa SO. Biodiesel Production from Nigerian Palm
270 Kernel Oil: Effect of KOH Concentration on Yield", Energy for Sustainable Development,
271 XI, 2007; 3:77-82.
272
- 273 [15] Chitra P, Venkatachalam P, Sampathrajan A. Optimization of experimental
274 conditions for biodiesel production from alkali catalysed transesterification of *Jatropha*
275 *curcas* oil. Energy for Sustainable Development. 2005; 9 (3): 13-18.
276
- 277 [16] Ma F, Hanna MA. Biodiesel production: a review. Bioresource Technol, 1999; 70 (1): 1–
278 15.
279
- 280 [17] Itodo IN, Oseni MI, Wergba C. A comparative study of the properties and yield of
281 biodiesel from soy and groundnut oils. Nig. J. Solar Ener. 2009; 21:124-128.
282
- 283 [18] Akbar E, Yaakob Z, Kamarudin SK, Ismail M, Salimon J. Characteristics and
284 composition of (*Jatropha curcas*) oil seed from Malaysia and its potential as biodiesel
285 feedstock. Eur. J. Sci. Res., 2009; 29(3):396-403.